


# PureWeld XL weldable TPE tubing

PureWeld XL TPE Tubing

## Features and benefits


- Reduces inventory and minimises fluid contact materials
- Full compendial data to USP <788> for sub-visible particulates
- EP 2.6.14, USP<85> for bacterial endotoxins
- Suitable for sterilization by Gamma irradiation
- Animal-derived content free (ADCF)



## Performance

### Pumping life

Pumping life at 2 bar discharge pressure



## Technical specifications

|                                   | PureWeld XL weldable TPE tubing   |
|-----------------------------------|---|
| Bore size                         | 0.5 - 25.4 mm   |
| Bore size                         | 0.02 - 1 in   |
| Wall thickness                    | 1.6 - 4.8 mm  |
| Wall thickness                    | 0.0625 - 0.1875 in  |
| Length                            | 15 - 152 m  |
| Colour                            | Colorless   |
| Transparency                      | Opaque  |
| Spallation                        | Very low  |
| Certification and compliance      | EC 1935/2004, FDA 21CFR177.1810, USP <661>, USP <788>, USP <85>, USP Class VI |
| Operating temperature range       | -20 to 80 °C  |
| Operating temperature range       | -4 to 176 °F  |
| Hardness, shore A (5sec)          | 65-73   |
| Specific gravity                  | 0.89-0.91 g/cm <sup>3</sup>   |
| UV resistance                     | Good  |
| Tear B                            | >30 kN/m  |
| Tear B                            | >171 ppi  |
| Ultimate tensile strength         | 63-180 bar  |
| Ultimate tensile strength         | 116 - 261 psi   |
| Ultimate tensile strength         | 8 - 18 MPa  |
| Elongation at break               | >450 %  |
| Tensile stress at 100% elongation | 2.4-3.5 Mpa   |
| Tensile stress at 100% elongation | 348 - 507 Psi   |
| Gas permeability rating           | Low   |
| Compression set                   | <80 %   |
| Water absorption                  | Low   |
| Gamma stability                   | 25 to 50kGy   |
| Sterilisation methods             | Gamma   |

ISO Hardness: ISO 868; Specific gravity: ISO2781; Tear B, Ultimate tensile strength, Elongation at break, Tensile stress at 100 % elongation; ISO37-2005. Values reported above are not intended for sales specification and some of the properties are not routinely measured.

## Materials of construction

|        | PureWeld XL weldable TPE tubing |
|--------|---------------------------------|
| Tubing | SEBS                            |

## Product codes

| PureWeld XL peristaltic pump tubing sizes available |       |      |      |              |
|---|-------|------|------|--------------|
| Bore  |       | Wall |      | Part number  |
| mm  | inch  | mm   | inch |              |
| 0.5   | 1/50  | 1.6  | 1/16 | 942.0005.016 |
| 1.6   | 1/16  | 1.6  | 1/16 | 942.0016.016 |
| 1.6   | 1/16  | 2.4  | 3/32 | 942.0016.024 |
| 2.4   | 3/32  | 1.6  | 1/16 | 942.0024.016 |
| 3.2   | 1/8   | 1.6  | 1/16 | 942.0032.016 |
| 4.8   | 3/16  | 1.6  | 1/16 | 942.0048.016 |
| 4.8   | 3/16  | 2.4  | 3/32 | 942.0048.024 |
| 6.4   | 1/4   | 1.6  | 1/16 | 942.0064.016 |
| 6.4   | 1/4   | 2.4  | 3/32 | 942.0064.024 |
| 8.0   | 5/16  | 1.6  | 1/16 | 942.0080.016 |
| 8.0   | 5/16  | 2.4  | 3/32 | 942.0080.024 |
| 9.6   | 3/8   | 2.4  | 3/32 | 942.0096.024 |
| 9.6   | 3/8   | 3.2  | 1/8  | 942.0096.032 |
| 9.6   | 3/8   | 4.8  | 3/16 | 942.0096.048 |
| 12.0  | 15/32 | 4.0  | 5/32 | 942.0120.040 |
| 12.7  | 1/2   | 3.2  | 1/8  | 942.0127.032 |
| 12.7  | 1/2   | 4.8  | 3/16 | 942.0127.048 |
| 15.9  | 5/8   | 3.2  | 1/8  | 942.0159.032 |
| 15.9  | 5/8   | 4.8  | 3/16 | 942.0159.048 |
| 19.0  | 3/4   | 4.8  | 3/16 | 942.0190.048 |
| 25.4  | 1     | 4.8  | 3/16 | 942.0254.048 |

All sizes of PureWeld XL tubing are available in 50ft (15m) coils. Custom sizes are available to order, as are other specific requirements.

Disclaimer: Watson-Marlow, Pumpsil, PureWeld, LoadSure, LaserTraceability, Bioprene and Marprene are registered trademarks of Watson-Marlow Limited. STA-PURE PCS and STA-PURE PFL and Style 400 are trademarks of WL Gore & Associates Inc. Please state the product code when ordering pumps and tubing.

[wmfts.com/global](http://wmfts.com/global)



01 May 2024